



PERFO COR

General Information

Perfo Cor is 440C martensitic stainless which is reinforced with molybdenum.

Chemical Composition

C %	Cr %	Mo %
1.05	15.00	3.50

Application Areas

- Cutlery
- Bearings
- Valve connection equipments
- Bushing

Heat Treatment

Preheating	Hardening	Annealing
760°C	1037 - 1093°C	900°C